

Pro-Seal PC-V Top Coat™

Polycarbon/Polycarbonate High Sheen Color-Fast Top Coating



PC-V Top Coat™ is a single component high sheen top coating that is stabilized for excellent actinic and U.V. resistance. **Polycarbon/polycarbonate integrated technology.*

- Easy to install
- Excellent abrasion resistance
- Color-fast over decades of outdoor exposure
- Easy to clean
- Available in high or semi-flat sheen

Applications

- Fusing top coat for longer surface life
- Water containment structures
- Exposed structural steel beams, joints, roofs, columns, etc.
- Curtain wall panels such as transite, insulating steel, etc.
- Exposed steel in sewage areas
- Metal fascia and other exposed architectural metal surfaces

Application Instructions: Surface must be dry, clean and free of all loose particulate and bond-breaking matter. For specific application instructions or guide specifications, contact Pro-Seal's Technical Department at 800.349.7325 or information@prosealproducts.com

Technical

Information	Value
Material	1 Part
Mix time	N/A
Appearance	Liquid
Pigments	Titanium Dioxide
Solids	34.8% weight 19% volume
Elongation	200%
Build per coat	1-2 mils dry
Application temperature	-35°F To 140°F
Flash point	51°F
Cure time to recoat	1 Hour
Full cure	24 Hours
Packaging:	55 Gallons

Technical Support: Contact our technical department at 800.349.7325, information@prosealproducts.com or visit our website www.prosealproducts.com for additional information.

Cautions: Keep out of reach of children. May cause skin or eye irritation. This product may be harmful if swallowed. Do not induce vomiting. Contact a physician immediately and always seek a physician's advice regarding first aid. Use only in commercial or industrial applications. Use only on intended surfaces. Contact manufacturer for specific application uses. See material safety data sheet for additional cautions.

Limited Warranty: We warrant our product to be free of defects in material and workmanship; and to be in accordance with our company quality control standards. All data, statements, and recommendations, made herein are based upon information we believe to be reliable, but are made without any representation, guarantee, or warranty of accuracy. Our products are sold on the condition that the user himself will evaluate them, as well as our recommendations, to determine their suitability for the user's own purpose before adoption. Also, statements regarding the use of our products or processes are not to be construed as recommendations for their use in violation of any patent rights or in violation of any applicable laws or regulations. Liability under any condition shall be limited to replacement of material only.