

Pro-Seal PPW™

Quick-Setting Grout



PPW™ is quick setting grout material for patching and repairing cracks in concrete or mortar. *Polycarbon/polycarbonate integrated technology

- Easy to use
- Minimal preparation required
- Sets in 3-5 minutes
- May be used in vertical applications when mixed properly
- May be rubbed into hairline cracks pre-treated with Pro-Seal DP-36®

Applications: Concrete Spall Repair, Tuck Pointing, Non Moving Joint Repair, Negative Side Repair and Crack Repair.

Application Instructions: Surface must be clean and free of all loose particulate and bond-breaking matter. For specific application instructions or guide specifications, contact us at 800.349.7325 or information@prosealproducts.com

Technical

Information	Value
Material	1 parts
Mix time	1-3 minutes
Set time	3-5 minutes
Appearance	Paste
Cure time (light traffic)	3-5 minutes
Full cure	28 days
Color	Gray
Coverage rate 50 lb pail	~850 cubic inches of mortar
Packaging:	55 lb pails

Specifications

ASTM	Test	Data (Typical)
C 109	Compressive strength	24 hrs 6,100 7 days 10,200 28 days 11,325
C 266	Set time	Initial: 1 minutes Final: 3 minutes
CSA		
A 23.2-6B	Tensile pull off	186 psi

Technical Support: Contact our technical department at 800.349.7325, information@prosealproducts.com or visit our website www.prosealproducts.com for additional information

Army Corps Of Engineers CRD-C621		
Test	Days	Value
Fluidity: plastic water content: 6 pints flow: 100 seconds expansion	3 Days	+ .02
	14 Days	+ .01
	28 Days	+ .01
Compressive Strength	1 Day	6,500 Psi
	3 Days	8,000 Psi
	7 Days	10,000 Psi
	28 Days	11,000 Psi
Fluidity: flow able water content: 7 pints flow: 130 Seconds expansion	3 Days	+ .01
	14 Days	+ .01
	28 Days	+ .01
Compressive Strength	1 Day	6,000 Psi
	3 Days	8,000 Psi
	7 Days	10,000 Psi
	28 Days	11,000 Psi
Fluidity: fluid water content: 8.3 pints flow: 30 seconds expansion	3 Days	+ .01
	14 Days	+ .01
	28 Days	+ .01
Compressive Strength	1 Day	4,500 Psi
	3 Days	7,000 Psi
	7 Days	8,500 Psi
	28 Days	10,000 Psi

* Data based on laboratory tested materials.

Cautions: Keep out of reach of children. May cause skin or eye irritation. This product may be harmful if swallowed. Do not induce vomiting. Always wear a dust mask when applying this product. Use in well ventilated areas. Contact a physician immediately and always seek a physician's advice regarding first aid. Use only in commercial or industrial applications. Use only on intended surfaces. Contact manufacturer for specific application uses. See material safety data sheet for additional cautions

Limited Warranty: We warrant our product to be free of defects in material and workmanship; and to be in accordance with our company quality control standards. All data, statements, and recommendations, made herein are based upon information we believe to be reliable, but are made without any representation, guarantee, or warranty of accuracy. Our products are sold on the condition that the user himself will evaluate them, as well as our recommendations, to determine their suitability for the user's own purpose before adoption. Also, statements regarding the use of our products or processes are not to be construed as recommendations for their use in violation of any patent rights or in violation of any applicable laws or regulations. Liability under any condition shall be limited to replacement of material only.

